



FILAMENT DATASHEET

MATERIAL: Carbonium CFPA

WE CARE ABOUT YOUR PRINTS

Suggested printing specs.	Value	Unit	Standard
Extruder Temperature	240° +/-10°	°C	Internal
Bed Temperature	100° +/-10°	°C	Internal
Print speed	40-50	mm/s	Internal
Fan	0-40	%	Internal
Minimum Nozzle Diameter	0,35	mm	Internal
Material Properties	Value	Unit	Standard
Density	1,07	g/cm ³	ISO 1183
Water Absorption	1,1	%	ISO 62
Tensile Modulus	8000	MPa	ISO 178
Melting Point DSC	178°	°C	ISO 3146
Flexural Modulus	6800	MPa	ISO 178
Volume Resistivity	1,00 e+11	ohm/cm	IEC 60093
Stress at break	110	MPa	ISO 527-2

DISCLAIMER

The Information presented herein has been compiled from sources considered to be dependable and is accurate to the best of our knowledge. However, since data, safety standards, and government regulations are subject to change and the conditions of handling and use, or misuse, are beyond our control, Sa2p/Treed Filaments makes no warranty expressed or implied, with respect to completeness or continuing accuracy of the information contained herein and disclaims all liability for reliance thereon.

User should satisfy himself that he has all current data relevant to his particular use.